




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b>  <b>B32B 17/02, F16L 59/08</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 90/09281</b>  <b>(43) International Publication Date:</b> 23 August 1990 (23.08.90)
<b>(21) International Application Number:</b> PCT/GB90/00262  <b>(22) International Filing Date:</b> 16 February 1990 (16.02.90)  <b>(30) Priority data:</b> 8903641.2      17 February 1989 (17.02.89)      GB  <b>(71) Applicant (for all designated States except US):</b> COUR- TAULDS PLC [GB/GB]; 18 Hanover Square, London W1A 2BB (GB).  <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only) :</b> GIDLEY, Roy, Joseph [GB/GB]; 33 Pennine Drive, Milnrow, Lancaster OL16 3HL (GB).  <b>(74) Agent:</b> NEWBY, John, Ross; J.Y. & G.W. Johnson, Fur- nival House, 14-18 High Holborn, London WC1V 6DE (GB).		<b>(81) Designated States:</b> AT (European patent), BE (European patent), CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), IT (European patent), JP, LU (European patent), NL (European patent), SE (European patent), US.  <b>Published</b> <i>With international search report.          Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

**(54) Title:** FLEXIBLE FABRIC THERMAL INSULATORS**(57) Abstract**

A laminated fabric suitable as a thermal insulator or fire barrier. The fabric comprises a layer (10) of a knitted glass fabric, to provide flexibility, and layers of heat reflecting materials (11), to reflect the heat, and woven glass fabric (12) to provide an effective thermal barrier.

***FOR THE PURPOSES OF INFORMATION ONLY***

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	ML	Mali
AU	Australia	GA	Gabon	MR	Mauritania
BB	Barbados	GB	United Kingdom	MW	Malawi
BE	Belgium	HU	Hungary	NL	Netherlands
BG	Bulgaria	IT	Italy	NO	Norway
BJ	Benin	JP	Japan	RO	Romania
BR	Brazil	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	LI	Liechtenstein	SN	Senegal
CH	Switzerland	LK	Sri Lanka	SU	Soviet Union
CM	Cameroon	LU	Luxembourg	TD	Chad
DE	Germany, Federal Republic of	MC	Monaco	TG	Togo
DK	Denmark	MG	Madagascar	US	United States of America
FI	Finland				

FLEXIBLE FABRIC THERMAL INSULATORSTechnical Field

This invention relates to flexible laminated fabrics which are suitable for use as fire barriers and thermal  
5 insulation materials.

British Standard BS 476 part 20 lays down certain standards which fire barriers have to meet to be acceptable. In certain cases there is a requirement that the barrier should retain its insulation performance for at  
10 least 30 minutes. Whilst in some cases products can be designed to meet this specification by making them thicker or more bulky there are applications where the increased weight per unit area, thickness and/or bulk are unacceptable. There is therefore a need for a lightweight flex-  
15 ible fabric barrier which will conform with the fire resistance standards but which is of reduced thickness and/or weight per unit area compared to prior art barriers and the present invention seeks to meet this need.

Summary of the Invention

20 According to the present invention, a laminated fabric comprises a first layer of knitted glass fabric, a second layer of heat reflecting material, a third layer comprising a woven glass fabric and a fourth layer comprising an abrasion resistant material.

25 Suitably the first layer is a weft knitted fabric, and the second layer is a material selected from the group comprising aluminium and stainless steel. Desirably the first layer is clad on each surface with a second, a third and a fourth layer.

30 The invention provides a flexible fabric which is lightweight, very flexible, and can be made quite thin and

still meet the above-mentioned British Standard specification.

#### Brief Description of Drawing

An embodiment of the present invention will now be described, by way of an example, with reference to the accompanying drawing, in which:

Figure 1 shows, schematically, a cross-section through a flexible fire barrier constructed in accordance with the present invention, and

10 Figure 2 shows a length of barrier material of the type shown in Figure 1, as a partly rolled-up blanket.

#### Description of Preferred Embodiment

Referring to Figure 1 of the drawing, a barrier 9 comprises a layer of weft knitted texturised glass fabric 15 10. This fabric is knitted from electrical grade glass filaments of approximately  $6\mu$  diameter to give a layer of approximately 8 mm thick.

Preferably, but not necessarily, the fabric 10 is leached in hydrochloric acid to remove impurities and thus 20 improve its temperature resistance.

A heat reflective layer 11, for example an aluminium foil, about  $15\mu$  thick is located adjacent each surface of the fabric 10. The aluminium layers 11 are not bonded to the fabric 10. Each aluminium layer 11 is preferably 25 bonded, using a neoprene or a silicone adhesive, to an outer layer of woven glass fabric 12. It is not absolutely necessary to bond the aluminium to the outer layer 12 at this stage of manufacture. The fabric-layer 12 is a plain weave using electrical grade glass filaments of about  $9\mu$  30 diameter. The outermost surface of each fabric layer 12 is

coated with a thin skin of silicone rubber 13 to provide abrasion resistance. The total thickness of the barrier shown in the drawing is about 12 mm, although various thicknesses can be produced using different diameters of  
5 glass filaments.

Various modifications can be made without departing from the invention. For example although the aluminium heat reflective layers 11 are shown in the drawing between the knitted fabric layer 10 and each woven fabric layer 12,  
10 the aluminium layers 11 could be provided on the outside surface of the woven layer 12. In this case, the silicone rubber 13 would be applied to the aluminium layers 11, and the aluminium layers 11 would be bonded to the surface of the woven layers 12. The silicone rubber could be omitted,  
15 in which case the glass fabric would be subjected to a vermiculite treatment.

In yet a further modification, a thicker barrier could be made by adding one or more layers of knitted glass fabrics similar to the layer 10. In this modification,  
20 heat reflective layers of aluminium could be located between knitted glass layers, although it may also be possible to do without heat reflective layers between the knitted glass layers and to use heat reflective layers applied to outer woven layers similar to those shown as 12  
25 in the drawing.

An important feature of a barrier 9 according to this invention is its flexibility without loss of its thermal insulation capabilities. A barrier when made in accordance with the embodiment shown in Figure 1 is flexible enough  
30 to be rolled onto itself (as shown in Figure 2) for storage and deployed as a fire barrier by unrolling it. Furthermore the barrier constructed in accordance with the embodiment illustrated also shows good potential as a thermal insulator for use in the building trade, for example in  
35 cavity wall thermal insulation and may provide acoustic

insulation as well.

Flexibility is imparted to the laminated barrier 9 by the use of knitted glass fabric which in itself is also an effective thermal barrier. In addition, the woven glass fabric, although not quite so flexible as a knitted fabric provides a good thermal screen. The aluminium further enhances the heat reflective ability of the barrier.

Other heat reflective materials could be used in place of aluminium for example stainless steel foil could be used.

CLAIMS

1. A laminated fabric comprising a first layer (10) of knitted glass fabric, a second layer (11) of heat reflecting material, a third layer (12) comprising a woven glass fabric and a fourth layer (13) comprising an abrasion resistant material.

2. A fabric according to claim 1, wherein the first layer (10) is a weft knitted fabric.

3. A fabric according to claim 1, wherein the second layer (11) is a material selected from the group comprising aluminium and stainless steel.

4. A fabric according to claim 1, wherein the first layer (10) is clad on each surface with a second (11), a third (12) and a fourth (13) layer.

5. A fabric according to claim 1, wherein there are two or more first layers (10).

6. A fabric according to claim 5, wherein there are two or more second layers (11).

7. A fabric according to claim 6, wherein a second layer (11) is interposed between the first layers (10).

8. A fabric according to claim 1, wherein the fourth layer (13) is resilient.

9. A fabric according to claim 8, wherein the fourth layer (13) is a silicone rubber.

10. A flexible fire-resistant barrier (9) formed from a rolled-up length of laminated fabric as claimed in claim 1.

$\frac{1}{1}$




FIG. 1




FIG. 2



# INTERNATIONAL SEARCH REPORT

International Application No PCT/GB 90/00262

## I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) \*

According to International Patent Classification (IPC) or to both National Classification and IPC

IPC<sup>5</sup>: B 32 B 17/02, F 16 L 59/08

## II. FIELDS SEARCHED

Minimum Documentation Searched <sup>7</sup>

Classification System |

Classification Symbols

IPC<sup>5</sup>

B 32 B, F 16 L

Documentation Searched other than Minimum Documentation  
to the Extent that such Documents are Included in the Fields Searched <sup>8</sup>

## III. DOCUMENTS CONSIDERED TO BE RELEVANT <sup>9</sup>

Category <sup>*</sup>	Citation of Document, <sup>11</sup> with Indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>
A	DE, A, 2451234 (VYZKUMNY USTAV PLETARSKY) 7 May 1975 see page 2, line 7 - page 4, line 24; claims 1-3; figure 2  --	1-3, 8, 10
A	EP, A, 0272793 (TECH TEXTILES LTD) 29 June 1988 see column 1, lines 30-54; column 3, lines 16-30; column 4, lines 33-38; claims 1,4-6,12,14; figure 1  --	1,2,9
A	DE, A, 2907707 (HOECHST) 4 September 1980 see page 5, line 23 - page 6, line 5, page 7, lines 13-31  -----	3,5-7

\* Special categories of cited documents: <sup>10</sup>

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"Z" document member of the same patent family

## IV. CERTIFICATE

Date of the Actual Completion of the International Search

21st May 1990

Date of Mailing of this International Search Report

14.06.90

International Searching Authority

EUROPEAN PATENT OFFICE

Signature of Authorized Officer

MISS T. TAZELAAR

**ANNEX TO THE INTERNATIONAL SEARCH REPORT  
ON INTERNATIONAL PATENT APPLICATION NO.**

GB 9000262

SA 34540

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on 13/06/90  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE-A- 2451234	07-05-75	None	
EP-A- 0272793	29-06-88	US-A- 4808465	28-02-89
DE-A- 2907707	04-09-80	None	